

**ATTAR TEST REPORT NUMBER: 13/7067.2**

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025. Accreditation Number: 2735

22 July 2013

**Total Pages: 1****DRY SLIP RESISTANCE**

Job No: M13/7067

<b>Prepared for:</b>	Whittle Waxes Pty Ltd 6/9 Pilgrim Court RINGWOOD VIC 3134		
<b>Attention:</b>	Darren Bell		
<b>Test Site:</b>	ATTAR, Unit 1, 64 Bridge Road, Keysborough.		
<b>Test Date:</b>	18 July 2013		
<b>Test Specimens, Size and Quantity:</b>	Coated Hardwood with Whittle Waxes Hardwax Oil x two coats, Classic, 670x225 mm, 1 off supplied.		
<b>Sampling and Direction of Test:</b>	Sampling conducted by client. Test direction parallel with grain of timber.		
<b>Test Personnel:</b>	Douglas Lehne		
<b>Preparation:</b>	Washed with pH neutral detergent, rinsed with water, then dried.		
<b>Fixed/Unfixed:</b>	Unfixed.		
<b>Air Temperature:</b>	21°C		
<b>Test Equipment:</b>	Tortus Floor Friction Tester; Tortus Model Mk III (with integral printer), Serial No: 318.		
<b>Test Standard:</b>	AS/NZS 4586: 2004 Slip resistance classification of new pedestrian surface materials – Appendix B.		
<b>Slider Rubber:</b>	Slider 96 (Four S) Batch No. 44		
<b>Classification Criteria:</b>	Refer Appendix 1 – Classification Criteria, attached.		
<b>Dynamic Coefficient of Friction</b>	<b>Run 1</b>	<b>Run 2</b>	<b>Mean</b> Rounded to 0.05
	0.64	0.63	0.65
<b>Classification:</b>	<b>F</b>		

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

**NOTE:** Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

**ATTAR**

Douglas Lehne  
Floor Slip Tester  
Approved Signatory

This report may not be reproduced except in its entirety.

**Page 1 of 1**